

SI8135W A/B

Silicone Potting Sealant

Premium Quality & Ultimate Service

Two Component Silicone Potting Adhesive

SI8135W A/B

■ Technical Data Table

TESTING ITEM	ESTING STANDARD	Part A	Part B
Color	Visual inspection	White liquid	Colorless or light yellow transparent
Viscosity, cps , 25°C	GB/T 10247-2008	1100 ± 300	80 ± 20
Density,g/cm ³ , 25°C	GB/T 15223-1994	1.10 ± 0.05	0.98 ± 0.02
Mixture ratio	Weight Ratio	A: B = 100: 18	
Viscosity of mixture,4#rotor,cps , 25°C	GB/T 10247-2008	900	
Operation time,mins , 25°C	GB/T 10247-2008	30	
Tack Free Time, 25°C	GB/T 10247-2008	60	
Characteristics after curing			
Cured appearance	Visual inspection	White soft elastomer	
Hardness, Shore A	GB/T 531-2008	14	
Tensile strength, Mpa	GB/T 528-2009	0.8	
Shear strength,MPa,Fe-Fe	GB/T 7124-2008	0.5	
Linear expansion coefficient, ppm	HGT 2625-1994	230	
Dielectric strength ,kV/mm, 25°C	GB/T 1695-2005	≥20	
Volume resistance,DC 500V, Ω·CM	GB/T 1692-92	1.0×10 ¹⁴	
Loss factor(1 MHz)	GB/T 1693-2007	<0.008	
Dielectric constant(1 MHz)	GB/T 1693-2007	<3.00	
Long time Application temperature, °C	GBT 20028-2005	-50~150	

PS: The operating time is tested based on the amount of glue 118g.

All data of the curing state are measured after 7 days of curing under the conditions of 25°C and 55%RH

SI8135W A/B

Silicone Potting Sealant

Premium Quality & Ultimate Service

■ Product Description

SI8135W A/B is suitable for potting protection of various components. It can be deep-cured, and the two components have good fluidity after mixing. The operating time can be adjusted according to the temperature of the curing agent. There is no need to use other primers before use, it has a good bonding effect to most materials, and is suitable for fixing accessories, waterproofing, dustproofing and preventing leakage.

■ Typical Applications

- Automotive electronics, modules
- Various sensors
- Power control module
- Water treatment ultrafiltration components

■ Packing Specification

- ◇ Part A: 20kg/drum;
- ◇ Part B: 5kg/pot
- ◇ Part A: 200kg/drum;
- ◇ Part B: 20kg/drum
- ◇ Customized Packing

■ Transport & Storage

- When stored at or below 25°C in the original unopened containers, this product has a usable life of 12 months from the date of production.

It's non-dangerous goods, can be transported as normal chemicals, CAUTION leakage during transport.

■ Key Features

- Two-component liquid silicone rubber, condensation and dealcoholization type
- Low viscosity, easy processing, strong operability
- Low hardening shrinkage, no corrosion and stress
- Excellent high-temperature electrical insulation and stability
- Excellent adhesion
- Good waterproof and moisture resistance

■ Directions for Use

1. Mixing uniformity in the packing before using, as there's part of filler sedimentation happens during storage.
 2. Mix Part A and Part B by 100:18 mass ratio, after evenly mixed, pouring directly into the components or modules as per requirements. It's recommended to slowly pour along the walls of the implements, so as to reduce the bubbles happens.
 3. Still the potted component to let out the bubbles. If possible, customers can vacuum and degas the mixed glue before potting. It can be cured directly at room temperature, usually within 3-4hr, the glue layer is elastic and can be turned over or handled.
- Vacuum defoaming can improve the performance of cured product.
 - Seal the remaining products tightly after use.
 - Low temperature will slow the curing speed, overheating will lead to curing speed too fast. Keep the constant temperature in workshop is

SI8135W A/B

Silicone Potting Sealant

Premium Quality & Ultimate Service

recommended.

- It's hard for SI8135W to cure if contact with sulfur, amine, organotin.

■ Attention of operation

- Keep away from Children
- Avoid contact with eyes and skin. If contact with

your skin, scrub first with soap water or alcohol, then rinse with water. If contact with your eyes, rinse with plenty of water, and seek medical treatment immediately.

- It is forbidden to build on the surface of the wet substrate.

■ Safety Operation Data

MSDS isn't included here. Please read TDS, MSDS and label carefully before operation. You can get MSDS from MAXTECH or other distributors, or mail to service center maxtech@shmaxtech.com

■ Warranty and Liability

All product properties and application details based on information believe to be reliable and accurate. But you still need to test its property and safety before application. The advice we supply don't apply in any circumstances. MAXTECH don't make assurance of any other applications outside the specification until MAXTECH supply a special written guarantee. MAXTECH is only responsible to replace or refund if this product is defective within the warranty period stated above. MAXTECH makes it clear that will not be liable of any accidents.

Special Notes: All recommendations concerning our products, including transportation, storage, and handling are based on our current knowledge and experience under normal conditions. In practical application, results may differ because of materials and actual site conditions change, our company won't guarantee or bear any legal responsibility. In order to ensure the bonding effect and the compatibility of products and materials, it is recommended to do the compatibility test or consult MAXTECH Technical Services before proceeding with the full application.